

[ABOUT DELPHION](#)
[PRODUCTS](#)
[NEWS & EVENTS](#)
[MY ACCOUNT](#)
[IP S](#)

[Log Out](#)
[Order Form](#)
[Work Files](#)
[View Cart](#)

The Delphion Integrated View

INPADOC Record

Title

Country

Kind

Inventor(s)

Applicant/Assignee

Inquire Regarding Licensing

Issued/Filed Dates

Application Number

IPC Class


ECLA Code

Priority Number(s)

Family

Other Abstract Info

Foreign References



Nominate this for the Gallery...

Other Views:
[Derwent...](#)

JP51055724A2: SHIKAYOKINGOKIN OYOBI SONOSEIZOHCHO

..P Japan

..2 Document Laid open to Public inspection

..YAJIMA YUTAKA [No Image](#)

..OKURIKI SHOTEN GOSHI

[News, Profiles, Stocks and More about this company](#)

May 17, 1976 / Nov. 12, 1974

..P1974000130153

..22C 5/02; A61C 13/00;

..one

..Nov. 12, 1974 **JP1974000130153**

..one

..HEMABS 085(14)099221N

..o patents reference this one

Number of Countries: 001 Number of Patents: 001

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Week
JP 51055724	A	19760517			197627	B

Priority Applications (No Type Date): JP 74130153 A 19741112

Abstract (Basic): JP 51055724 A

Dental alloy contains 68-96% Au and 1-10% Co, with 0-31% of ≥ 1 of Ag, Cu, Zn, Pd, Ir and Rh. The alloy is heated to 800-1000 degrees C solid-soln. treated, and then age-hardened by heating to 300-500 degrees C. With melting point low at 1000 degrees C, casting is easy. Temp. difference between the m.pt. and coagulation point is 28-60 degrees C, so segregation is not produced by quenching. Props. are not inferior to conventional Pt-contg. Au alloy. Hardness after solid soln. treatment is soft at 130-150, giving good machinability. After age-hardening hardness is 240-280.

Title Terms: DENTAL; GOLD; ALLOY; CONTAIN; COBALT; OBTAIN; REDUCE; COST; AGE; HARDEN

Derwent Class: M26; P32

International Patent Class (Additional): A61C-013/00; C22C-005/02

File Segment: CPI; EngPI

?

COST

25oct01 13:15:58 User113120 Session D532.2

\$11.26 0.478 DialUnits File351

\$6.48 2 Type(s) in Format 2

\$6.48 2 Types

\$17.74 Estimated cost File351

\$0.60 INTERNET

\$18.34 Estimated cost this search

\$18.96 Estimated total session cost 0.642 DialUnits

?

Return to logon page!